




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : H01M 4/58	A1	(11) International Publication Number: WO 95/07551 (43) International Publication Date: 16 March 1995 (16.03.95)
(21) International Application Number: PCT/US94/10181 (22) International Filing Date: 9 September 1994 (09.09.94)	(81) Designated States: AU, BR, BY, CA, JP, KR, NZ, RU, US. European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(30) Priority Data: 5-226040 10 September 1993 (10.09.93) JP (71) Applicant (for all designated States except US): HYPERION CATALYSIS INTERNATIONAL, INC. [US/US]; 38 Smith Place, Cambridge, MA 02138 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): IKEDA, Koji [JP/JP]; 4-13-6, Narusedai, Machida-shi, Tokyo (JP). HAUSSLEIN, Robert, W. [US/US]; 20 Slogum Road, Lexington, MA 02173 (US). HOCH, Robert [US/US]; Rural Route 1, Box 422, Hensonville, NY 12439 (US). (74) Agents: EVANS, Barry et al.; Curtis, Morris & Safford, 530 Fifth Avenue, New York, NY 10036 (US).		Published <i>With international search report.</i>
(54) Title: LITHIUM BATTERY WITH ELECTRODES CONTAINING CARBON FIBRILS  (57) Abstract A lithium battery characterized in that the anode (1) is formed from a carbon fibril material comprised of an aggregate of fibrils or non-aggregated mass of fibrils having an average particle diameter of 0.1 to 100 microns in which fine, filiform carbon fibrils of 3.5 to 75 nm in diameter are intertwined with each other, and fibrils being intercalated with lithium. The cathode (3) also contains carbon fibrils.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

LITHIUM BATTERY WITH ELECTRODES CONTAINING CARBON FIBRILS

FIELD OF THE INVENTION

This invention relates to a lithium battery in which carbon fibrils are used as an anode and/or cathode in a lithium secondary battery.


BACKGROUND OF THE INVENTION

A great deal of research has been conducted on lithium secondary batteries in which metallic lithium is used as the negative electrode because high voltage and high energy density are anticipated. A family of batteries, called variously lithium ion or rocking chair or swing systems, has been developed which include a carbon anode into which lithium intercalates. The ability to intercalate lithium is critical. Classically this requires a relatively good graphite structure. The intercalate is a true compound corresponding to a composition of C_6Li . It thus has safety and other advantages over a metallic lithium anode. However, the problem with batteries in which metallic lithium is used for the negative electrode is that cycle life is decreased because of reactions between the lithium and the solvent during charging and because of dendrite growth.

In order to eliminate this problem, studies have been conducted of Li-Al alloy and of various types of carbon fiber materials as negative electrode materials. However, new problems such as decrease in mechanical strength and deterioration of self-discharging characteristics have arisen with these materials.

As to the "rocking chair" cell, lithium is the only ionic species moving back and forth between the electrodes during charging and discharging. Specifically, during charging, intercalated lithium ions from the cathode e.g., $LiMn_2O_4$, move through the electrolyte to the anode where they pick up an electron in the process of intercalating the carbon. During discharge the reverse reaction takes place, i.e., the

uncharged lithium in the carbon loses an electron to the external circuit as it ionizes to Li^+ which migrates to and enters the cathode concurrent with local reduction of the oxide lattice by an electron from the external
5 circuit. The half cell reaction are shown below doing discharge.



10

The prior art lithium ion system is characterized by an intercalatable carbon anode and an intercalatable variable valence metal oxide cathode usually also admixed with carbon for conductivity. It is
15 the use of the carbon anode that sets the rocking chair system apart from earlier configurations using lithium metal anodes. These latter suffered from safety problems related to dendrite formation, flaking and spalling of lithium metal, leading, in turn to dangerously high
20 reaction rates and to side reactions with the electrolyte. These safety problems have been largely sidestepped by the absence of a bulk lithium phase.

Development of new more oxidation resistant electrolytes and, longer range, the development of
25 polymer electrolytes also contributes to safer Li cells. Nevertheless, these batteries utilize very reactive electrode materials and systems. Studies of even the Li intercalation electrode suggest it must be properly engineered to avoid runaway reaction under damage or
30 short circuit conditions.

Although both electrodes of the lithium ion cell use carbon, these carbons, like most electrode materials, were selected from those commercially available. That neither anode nor cathode performance
35 was satisfactory is seen from the poor power density and from the poor approach to theoretical energy density. The lithium ion battery as presently available has

commercial utility only because of its inherent thermodynamics and rather in spite of less than optimal kinetics and engineering.

A target use for fibrils is electrodes and current collectors. Fibrils are ca. 100Å diameter, catalytically grown, graphitic fibers, typically several microns long. While fibrils are graphitic, geometric constraints force some differences with pure graphite. Like graphite, fibrils are composed of parallel layers of carbon but in the form of a series of concentric tubes disposed about the longitudinal axis of the fibers rather than as multi-layers of flat graphite sheets. Thus, because of the geometric constraints in the narrow diameter of the fibrils, the graphite layers cannot line up precisely with respect to the layers below as flat graphite sheets can. Convergent beam electron diffraction has confirmed that the (002) graphitic planes are oriented along the tube axis with high crystallinity.

The structure of fibrils compares quite closely with the much studied buckytubes. However, unlike buckytubes, fibrils are produced as indispersable aggregates uncontaminated with amorphous carbon allowing fibrils to be fashioned into electrode structures with only minimal processing. The fibrils are grown by contacting catalyst particles with gaseous hydrocarbon in a hydrogen rich atmosphere. Their diameters are determined by the size of the catalyst particles and average 7-12 nanometers. Lengths are several micrometers. They are hollow tubes with wall thicknesses 2 to 5 nanometers. The walls are essentially concentric tubes of individual graphite layers rolled into cylinders. At intervals along the length of a fiber some of the inner layers may curve into hemispherical cepta spanning the hollow interior. Near these, the walls may for a short distance change into nested cones. These reflect changes in the catalyst/carbon interface during growth of the fibril. Unlike other catalytic vapor grown carbon fibers

they are free of less organized pyrolytic carbon on their surfaces.

Buckytubes, however, are grown by condensation of carbon vapor in an arc. They usually have a wider
5 distribution of diameters from single layer walls to many
tens of layers. The arrangement of graphite layers in
the walls is very similar to fibrils. Some have only
concentric cylinders (or polygonal cross sections).
Others also have septa and nested cones. It is likely
10 that some buckytubes are grown catalytically on catalyst
particles derived from impurities in the source carbon or
from the apparatus. It is not yet certain beyond doubt
that any are self assembled without catalyst - spark
temperatures are sufficient to vaporize iron or other
15 particles after growth. Less organized carbon is
deposited at the same time in the form of polygons or
turbostratic carbon some of which may coat the
buckytubes.

As would be expected from their structure and
20 similarity to graphite, fibrils are conductive. While
the conductivity of individual fibrils is difficult to
measure, a recent attempt has yielded an estimated
resistivity value of $9.5 (\pm 4.5) \text{ m}\Omega\text{cm}$, a resistivity
slightly higher than typically measured for graphitized
25 carbon, but consistent with what has recently been
recently measured for buckytubes.

Fibrils can be assembled into macrostructures
composed of interconnected fibril nanotubes, similar to
felt mats. The large number of contacts between
30 individual, conductive fibrils in the fibril mat results
in mats with high conductivities as well.

The porosity of homogeneous fibril mats is
determined by overall mat density. Porosity can be
further modified by co-slurrying fibrils with macrofibers
35 (e.g., glass or carbon) before formation of the mat.
This technique for forming both homogenous and co-
slurried fibril mats is both convenient on the laboratory

scale and is readily amenable to scale-up using fiber wet-laying (e.g., paper making).

Because of their small diameter, fibrils have a surface area of ca. $200\text{m}^2/\text{g}$ as determined by BET measurement. The value for the surface area can also be arrived at by calculation based on average fibril dimensions. This agreement between calculation and the BET measurement demonstrates that the $200\text{m}^2/\text{g}$ is all on the external surface of the fibrils. Analytical electrochemistry of fibril mat electrodes demonstrate that all of the fibril surface area is available for electrochemical processes. For example, the double layer charging capacitance of fibril mat electrodes varies linearly with the mass of fibrils in the electrode over a wide range of fibril mat densities. Fibrils allow for a combination of constant pore size and high surface area that is not available in other conductive carbons.

Such open nets of fibrils impose their high external surface area and consequent electrochemical availability on any chemical system that can be deposited on or physically entangled within mats of them.

Currently available lithium ion batteries use an intercalatable carbon as the anode. The maximum energy density of such batteries corresponds to the intercalation compound C_6Li , with a specific capacity of 372 A-hours/kg .

The ability to intercalate lithium is critical. Classically, this requires a relatively good graphite structure. This intercalate is a true compound corresponding to a composition of C_6Li .

OBJECTS OF THE INVENTION

The objective of this invention is to solve the aforementioned problems of the conventional technology and to provide a lithium battery whereby decrease in cycle life due to reactions between the negative electrode and the solvent and due to formation of

dendrites is inhibited and with which there are superior self-discharging characteristics.

Another object is to provide a lithium battery using Geus fibrils and lithium intercalates.

5 Another object is to explore improvements in performance of lithium ion batteries through use of fibril nanotubes as the current collector for both electrodes.

Yet another object is to achieve high power
10 density in lithium rechargeable cells possible by exploiting the high accessible surface area of fibrils ($200 \text{ M}^2/\text{g}$), formed into a three dimensional conductive networks. Lithium will be deposited in the intercalatable electrode structures i.e. carbon at the anode,
15 LiMn_2O_4 or some other redox system at the cathode - in such a way that no portion of the intercalatable structures will be more than a few hundred Angstroms from both the electrolyte interface and the fibril network itself which serves as current collector and structural
20 support.

These and other objects, features and advantages of the invention will become readily apparent from the ensuing description, and the novel features will be particularly pointed out in the appended claims.

25 SUMMARY OF THE PRESENT INVENTION

The invention is directed to a lithium battery characterized in that one or both electrodes are formed using a carbon fibril material comprised of an aggregate of fibrils having an average particle diameter of 0.1 to
30 $100 \mu\text{m}$ in which fine, filiform carbon fibrils of 3.5 to 75 nm in diameter are intertwined with each other.

It is also now believed that non-aggregated fibrils such as are disclosed in U.S. Patent Application Serial No. 08/057,328, filed May 5, 1993, the disclosure
35 of which is hereby incorporated by reference may be used in the electrodes of the invention.

In a preferred embodiment the anode is a carbon fibril aggregate or non-aggregated fibril mass intercalated with lithium.

BRIEF DESCRIPTION OF THE DRAWINGS

5 The invention will be understood more clearly and fully from the following detailed-description, when read with reference to the accompanying figures, in which
10 Fig. 1 is a cross-sectional view of one example of a battery in this invention. As shown in Fig. 1, 1 is designated as a negative electrode sheet; 2 is a separator; and 3 is a positive electrode sheet.

DETAILED DESCRIPTION OF THE INVENTION

15 The invention is broadly directed to a lithium battery characterized in that one or both electrodes are formed using a carbon fibril material.

The electrodes are formed using a carbon fibril material comprised of an aggregate or non-aggregated mass of fibrils having an average particle diameter of 0.1 to 100 μm in which fine, filiform carbon fibrils of 3.5 to 20 75 nm in diameter are present.

The spinel LiMn_2O_4 appears to be the best of the variable valence metal cathode systems known. In order to exploit the advantages of fibrils one then deposits lithiated manganese dioxide on or within them.

25 The conventional synthesis of LiMn_2O_4 involves oxidation chemistry incompatible with fibrils. Low temperature syntheses are conducted.

When precipitation is carried out in the presence of a slurry of fibrils and the product filtered, 30 the product should be a fibril mat containing "islands" of LiMn_2O_4 , necessarily very small because of the small spaces within the mat Hyperion has carried out a program aimed at deposition of MnO_2 in fibril electrodes using a similar approach and yielding fibril mats with very small 35 MnO_2 crystallites disposed within them. TEM shows that such a mat has MnO_2 inclusions of about 100 Å size. The desired LiMn_2O_4 looks similar.

It has been shown that batteries comprising lithium intercalates in the anode is possible. Successful lithium batteries made up of Geus (fishbone) fibrils and lithium intercalates as anodes are also
5 within the scope of the invention.

Kinetics and energetics of lithium storage are studied on carbonized electrode materials. Fibril/carbon electrodes are evaluated by both potentiostatic and galvanostatic methodologies to determine the energetics
10 and kinetics of lithium incorporation and release in standard three-electrode reference cells using $\text{LiClO}_4/\text{PC}/\text{DEM}$ and a lithium metal counter/reference. Fibril/carbon electrodes are evaluated over a wide range of charge and discharge rates. Electrode candidates that
15 show highest capacities or charge/discharge rates are further evaluated for cycle life. Lithiated manganese dioxide are prepared using precipitation methodologies.

The benefits of the invention are those that flow from major improvements in rechargeable portable
20 energy storage. Near term, the target is portable electronics, in which market available lithium ion batteries are beginning to compete with more established nickel cadmium and nickel metal hydride batteries. Longer term, the target is the electric vehicle.
25 Clearly, lithium batteries show advantages over traditional lead-acid systems. Rocking chair batteries already have far higher energy density, one of the critical performance parameters for EV.

Fibrils have been shown to offer both high
30 surface area and controlled porosity to help reduce diffusional resistances. This characteristic may produce better density at constant energy density.

One also expects to see improvements in battery life from fibril based electrodes. For example, because
35 the spinel is not relied upon as the mechanical basis of this electrode, processes leading to disintegration of LiMn_2O_4 should become unimportant. Pieces as small as

100Å are easily retained within the electrode and should continue to contribute to the electrochemistry.

Another basis for improvements in life using fibrils as the carbon component of the anode stems from their lack of residual oxygen on edge carbons, fibrils are produced in a highly reducing atmosphere. Their handling can be managed to keep the level of chemically bound oxygen as low as necessary. Such bound oxygen has been implicated as catalysts of damaging electrolyte reactions.

Another unquantifiable benefit would derive from replacement of non-rechargeable primary cells in consumer use with rechargeable lithium ion cells. Although rechargeable and AA, C and D cells have been available for some time, they have not found consumer acceptance. A lithium ion cell, if it had sufficiently high energy density, i.e., were significantly lighter than a conventional alkaline MnO_2 cell, could be the key to consumer acceptance.

The diameter of the carbon fibrils that are used in this invention should be 3.5 to 75 nm, and, preferably, 5 to 30 nm and their length should be at least greater than 5 times their diameter, and preferably, 10^2 to 10^4 times their diameter.

When the diameter of the carbon fibrils exceeds 75 nm, their effect in providing conductivity is decreased. When it is less than 3.5 nm, the carbon fibrils may scatter and become difficult to handle. When the length of the carbon fibrils is less than 5 times their diameter, conductivity is reduced.

An aggregate is formed in which the carbon fibrils are fine and filiform and in which they are intertwined with each other. The average particle diameter of the aggregate should be 0.1 to 100 μm , preferably, 0.2 to 50 μm , and, more preferably, 0.2 to 30 μm . When the average particle diameter exceeds 100 μm , a mixture with binder powder tends to be insufficient

when the aggregate is used as the negative electrode of a lithium battery. When the average particle diameter is less than $0.1 \mu\text{m}$, infiltration of the electrolytic solution does not readily occur and the lithium ion intercalation reaction does not readily occur when the aggregate is used as the negative electrode of a lithium battery.

The 90% diameter (d_{90}), which is the index of distribution of the aggregate, should be less than 100 m, preferably, less than 80 m, and, more preferably, less than 50 m. Further, the 90% diameter is less than 7.5 times the average particle diameter.

The average particle diameter (d_m) and the 90% diameter (d_{90}) in this invention are defined so as to satisfy the relationships indicated in the following formulas. Here, d_{\min} is taken as the minimum particle diameter and d_{\max} is taken as the maximum particle diameter in the particle size distribution in which the volumetric ratio V_d of the particle diameters d is taken as the probability variable.

Formula 1:

$$0.5 = \sum_{d_{\min}}^{d_m} V_d \quad \text{or} \quad 0.5 = \sum_{d_m}^{d_{\max}} V_d$$

Formula 2:

$$0.9 = \sum_{d_{\min}}^{d_{90}} V_d$$

The aspect ratio of the carbon fibrils that form the carbon fibril aggregate should ordinarily be greater than 5, preferably, greater than 100, and, more preferably, greater than 1000. In addition, the fibrils are ordinarily tubular with a hollow core.

Moreover, these carbon fibrils should not have a continuous thermal carbon layer and should have several

graphite layers parallel to the fibril axis. The proportion of the surface area that is coated with the aforementioned thermal carbon coating should ordinarily be less than 50%, preferably, less than 25%, and, more preferably, less than 5%.

The carbon fibrils that are used in this invention can be obtained, for example, using carbon fibrils manufactured by the method described in Japanese Patent Application No. 2-503334 [1990] as the raw material. This material may be use in unaltered form or be subjected to chemical or physical treatment, after which it is subjected to pulverization treatment. The chemical or physical treatment may be carried out before or after the pulverization treatment.

Examples of physical or chemical treatments of the carbon fibrils include oxidation with nitric acid, oxidation with ozone, organic plasma treatment, coating with resins such as epoxy resins and treatment with coupling agents such as organic silicon and titanium compounds.

The pulverization apparatus may be, for example, a pneumatic grinder (jet mill) or an impact grinder. Because these grinders can be operated continuously and the quantity treated per unit time is greater than that with a ball mill or a vibrating mill, pulverization costs can be lowered. In addition, a uniform carbon fibril aggregate of a narrow particle size distribution can be obtained by installing a classifying mechanism in the grinder or by installing a classifier such as a cyclone in the line.

Determination of the particle diameter of the aggregate was performed as follows. The carbon fibril material was introduced into an aqueous solution of a surfactant and was treated with an ultrasonic homogenizer to form an aqueous dispersion. Determination was made using a laser diffraction scattering type particle size distribution meter with this aqueous dispersion as the

test material. The carbon fibril material was mixed with binder powder and the mixture was kneaded, after which it was molded to form a sheet. This sheet was used as the negative electrode. There are no particular limitations on the composition of the binder, and polyethylene or polytetrafluoroethylene can be used.

There are no particular limitations on the composition of the positive electrode. For example, an oxide or sulfide of vanadium, manganese, molybdenum, niobium, titanium or chromium can be used as the active substance, graphite can be used as the conductive material and polytetrafluoroethylene can be used as the binder. These materials can be kneaded to form a sheet, after which lithium can be carried on it as a result of formation.

Further, formation of extended surface area electrodes via electropolymerization and subsequent pyrolysis to yield a disordered carbon, but with higher surface area is possible. The extended surface here may be in the form of flat polymeric ribbons. Certainly, it is the first description of an extended surface disordered carbon based on fibrils. The use of Geus fibrils is available as a composition of the positive electrode.

There are no particular limitations on the composition of the electrolytic solution. For example, it can be prepared by using lithium perchlorate, lithium thiocyanate or lithium borofluoride as the support electrolyte, with propane carbonate, dimethoxyethane and tetrahydrofuran being used individually or in mixtures as the solvent.

There are no particular limitations on the separator. For example, polypropylene nonwoven fabric can be used.

The invention will be more fully described and understood with reference to the following examples which are given by way of illustration.

Example 1

A carbon fibril material comprising a carbon fibril diameter of 13 nm and having an average particle diameter of the aggregate of 3.5 μm , and of which the 90% diameter was 8.2 μm with a polyethylene binder were mixed at a weight ratio of carbon fibril material and polyethylene binder of 80:20. The mixture was kneaded, and then molded into a sheet to make the negative electrode.

Cr₃O₈, acetylene black and tetrafluoroethylene were mixed at a weight ratio of Cr₃O₈, acetylene black and tetrafluoroethylene of 40:40:20 and the mixture was kneaded, after which it was molded into a sheet to make the positive electrode.

A 1 M propylene carbonate solution of lithium perchlorate was prepared as the electrolyte. A propylene nonwoven fabric impregnated with this electrolyte was inserted between the positive electrode sheet and the negative electrode sheet which were then housed in a case, making a battery of the structure shown in Figure 1.

The charge-discharge cycle characteristics of the battery that was obtained were evaluated on the basis of the degree of deterioration, C/Co (%), from the initial capacity value, Co (mAh), when charging for 6 hours at a constant voltage of 3V and continuous discharge for 6 hours at a constant resistance of 10 k Ω were repeated at room temperature (25°C).

Self-discharging characteristics were evaluated by studying the degree of deterioration, C/Co (%), from the initial capacity values, Co (mAh), when a battery charged at room temperature (25°C) was stored at room temperature (25°C).

The results of the charge-discharge cycle characteristics of the battery versus C/Co (%), and self-discharging characteristics versus C/Co (%) are tabulated in Table 1 below.

[Table 1]

5	Charge-discharge cycle characteristics	C/C ₀ (%)
	(cycles) 100 200 500 1000	98 95 92 90
10	Self-discharging characteristics	C/C ₀ (%)
15	(days) 10 50 100	98 95 90
20		

The lithium battery of this invention had a long charge-discharge cycle life and also had superior self-discharging characteristics.

The carbon fibril material that is used in this invention is an aggregate of fine, filiform carbon fibrils, for which reason there is smooth infiltration of electrolytic solution when it is used as the negative electrode in lithium batteries. Moreover, because it has a large effective surface area, the lithium ion insertion reaction is effected uniformly and rapidly throughout the entire negative electrode. For this reason, reactions between the negative electrode and the solvent and formation of dendrites are controlled to a greater extent than with conventional carbon fibril materials and charge-discharge cycle life and self-discharging characteristics are improved.

Example 2

Example 1 was repeated using Geus (fishbone) fibrils. Similar results were obtained.

Having thus described in detail preferred
5 embodiments of the present invention, it is to be
understood that the invention defined by the appended
claims is not limited to particular details set forth in
this description as many variations thereof are possible
without departing from the spirit or scope of the present
10 invention.

WHAT IS CLAIMED IS:


1. A lithium battery characterized in that the anode is formed using a carbon fibril material comprised of an aggregate of fibrils or non-aggregated
5 mass of fibrils having an average particle diameter of 0.1 to 100 μm in which fine, filiform carbon fibrils of 3.5 to 75 nm in diameter are present, said fibrils being intercalated with lithium.

2. A lithium battery characterized in that
10 the anode is formed using a carbon Geus (fishbone) fibril material comprised of Geus (fishbone) fibrils having an average particle diameter of 0.1 to 100 μm in which fine, filiform carbon Geus (fishbone) fibrils of 3.5 to 75 nm in diameter are present, said Geus (fishbone) fibrils
15 being intercalated with lithium.

3. A lithium battery including a carbon fibril-containing cathode and an anode containing an aggregate of fibrils or non-aggregated mass of fibrils having an average particle diameter of 0.1 to 100 μm in
20 which fine, filiform carbon fibrils of 3.5 to 75 nm in diameter are present, said fibrils being intercalated with lithium.

4. A lithium battery including a carbon fibril-containing cathode and an anode containing Geus
25 (fishbone) fibrils having an average particle diameter of 0.1 to 100 μm in which fine, filiform carbon Geus (fishbone) fibrils of 3.5 to 75 nm in diameter are present, said Geus (fishbone) fibrils being intercalated with lithium.

[Figure 1]



INTERNATIONAL SEARCH REPORT

International application No.
PCT/US94/10181

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) :H01M 4/58

US CL :429/218

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 429/218, 212, 232

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched


Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US, A, 4,663,230 (Tennent) 05 May 1987, col. 4, line 48- col. 5, line 7, col. 7, line 61- col. 8, line 5.	1-4
Y	US, A, 5,225, 296 (Ohsawa et al.) 06 July 1993, abstract and claim 19.	3,4
Y	US, A, 4,980,250 (Takahashi et al.) 25 Dec 1990, col. 3, lines 5-12.	1-4
A,P	US, A, 5,302,474 (Shackle) 12 April 1994, col. 2, lines 57-60.	1-4
A,P	US, A, 5,246,794 (Blomgren et al.) 21 September 1993, col. 1, lines 45-54.	1-4

☒ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
E earlier document published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means	
P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search 01 DECEMBER 1994	Date of mailing of the international search report DEC 30 1994
Name and mailing address of the ISA/US Commissioner of Patents and Trademarks Box PCT Washington, D.C. 20231 Facsimile No. (703) 305-3230	Authorized officer  CAROL CHANEY Telephone No. (703) 308-0661

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US94/10181

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	Patent Abstracts of Japan, Volume 14, No. 211 (C-715), page 77, for Kokai No. 2-47347 (Morimoto) 16 February 1990, entire abstract.	1-4

THIS PAGE BLANK (USPTO)